"Express Mail" ma	ailing label number	EL562522779US
Date of Deposit:	1/3/01	

Our File No. 659/866 K-C Reference No.: 13,308.1

IN THE UNITED STATES	PAIENI AND	IRADEMARK	OFFICE
In re Application of:)		

mre ripphoducti on	\ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \
Jones et al.)
Continuation of Filing Date: 11/18/98) Examiner: Not Assigned) Group Art Unit No.: Not Assigned
For: SOFT HIGHLY ABSORBENT PAPER PRODUCT CONTAINING KETENE DIMER SIZING AGENTS)))

Assistant Commissioner for Patents Washington, D.C. 20231

Dear Sir:

PRELIMINARY AMENDMENT

This is a Preliminary Amendment to the above-referenced patent application, which is filed concurrently herewith.

In the Specification:

In the Specifications, please insert as the first line on page 1 the following:

--This is a continuation of serial number 09/195,579 filed 11/18/98 the disclosure of which is incorporated herein by reference--.

In the Claims

Please amend the claims as follows:

1.(Amended) A soft highly absorbent tissue product comprising long [and short] paper making fibers and a ketene dimer sizing agent.

and the second s

- 2.(Amended) A soft absorbent paper <u>tissue</u> product comprising paper making fibers and at least about 1 pound [per ton] of a ketene dimer sizing agent <u>per ton of paper product</u>, the tissue having an absorbency rate [test] of less than about 10 seconds.
- 3. (Amended) The paper product of claim 2 in which the product comprises [a] three[-]_layers [base sheet].
- 4. (Amended) A soft absorbent tissue sheet comprising: a first layer and a second layer; the first layer comprising predominately long paper making fibers and the second layer comprising predominantly short paper making fibers; at least one of the layers further comprising a ketene dimer sizing agent and a surface active agent; and the layer comprising the ketene dimer and <u>surface active</u> [wetting] agent being [readily] wetable by water.
- 7.(Amended) The soft tissue sheet of claim 4, in which the absorbency rate [test] is less than about 10 seconds.
- 9.(Amended) An absorbent paper sheet having improved softness comprising: a first sheet surface and a second sheet surface; a layer comprising paper making fibers; the layer having a surface; the surface of the layer corresponding to a surface of the paper sheet; the surface of the layer having a ketene dimer sizing agent therein; the surface of the sheet having a surface active agent therein; and the wetability of the sheet being equivalent to a sheet of [similar] the same composition but not having the ketene dimer sizing agent [and wetting agent] therein.
- 16. (Amended) The paper sheet of claim 9 comprising a second and a third layer; [the surface of the layer corresponding to the first sheet surface] and the surface of the third layer corresponding to the second sheet surface.
- 22. (Amended) The soft highly absorbent paper product of claim 21, in which there are at least 1 ½ pounds [per ton] of the sizing agent per ton of paper product, and the product has a water absorbency rate of less than 10 seconds.

A copy of the claims in clean form as amended by this Preliminary Amendment is attached hereto.

Respectfully submitted,

Glen P. Belvis

BRINKS HOFER GILSON & LIONE P.O. BOX 10395 CHICAGO, ILLINOIS 60610 (312) 321-4239

Registration No. 31,735 Attorney for Applicant

659/866 CLEAN COPY OF CLAIMS AS AMENDED BY PRELIMINARY AMENDMENT

CLAIMS

- 1. (as amended by Preliminary Amendment) A soft highly absorbent tissue product comprising long paper making fibers and a ketene dimer sizing agent.
- 2. (as amended by Preliminary Amendment) A soft absorbent paper tissue product comprising paper making fibers and at least about 1 pound of a ketene dimer sizing agent per ton of paper product, the tissue having an absorbency rate of less than about 10 seconds.
- 3. (as amended by Preliminary Amendment) The paper product of claim 2 in which the product comprises three layers.
- 4. (as amended by Preliminary Amendment) A soft absorbent tissue sheet comprising: a first layer and a second layer; the first layer comprising predominately long paper making fibers and the second layer comprising predominantly short paper making fibers; at least one of the layers further comprising a ketene dimer sizing agent and a surface active agent; and the layer comprising the ketene dimer and surface active agent being wetable by water.
 - 5. The soft tissue sheet of claim 4, in which the sheet is creped.
 - 6. The soft tissue sheet of claim 4, in which the sheet is through dried.
- 7. (as amended by Preliminary Amendment) The soft tissue sheet of claim 4, in which the absorbency rate is less than about 10 seconds.
 - 8. The tissue of claim 4 in which the tissue sheet comprises a third layer.

- 9. (as amended by Preliminary Amendment) An absorbent paper sheet having improved softness comprising: a first sheet surface and a second sheet surface; a layer comprising paper making fibers; the layer having a surface; the surface of the layer corresponding to a surface of the paper sheet; the surface of the layer having a ketene dimer sizing agent therein; the surface of the sheet having a surface active agent therein; and the wetability of the sheet being equivalent to a sheet of the same composition but not having the ketene dimer sizing agent therein.
 - 10. The paper sheet of claim 9, in which the sheet is a bath tissue.
- 11. The paper sheet of claim 10, in which the bath tissue has a second layer comprising paper making fibers.
 - 12. The paper sheet of claim 9, in which the sheet is a towel product.
- 13. The paper sheet of claim 12, in which the towel product has a second layer comprising paper making fibers.
 - 14. The paper sheet of claim 9, in which the sheet is a facial tissue.
- 15. The paper sheet of claim 14, in which the facial tissue has a second layer comprising paper making fibers.
- 16. (as amended by Preliminary Amendment) The paper sheet of claim 9 comprising a second and a third layer; and the surface of the third layer corresponding to the second sheet surface.
- 17. An absorbent paper sheet having improved softness comprising cellulose paper making fibers and a ketene dimer sizing agent and a surface active agent; the sizing of the sheet being no greater than about three times the sizing of a sheet of similar composition but not having the ketene dimer sizing agent and surface active agent.
- 18. A method of making a soft highly absorbent paper sheet product having improved softness comprising:

- (a) forming an aqueous slurry comprising paper making fibers in a pulper;
- (b) combining a the ketene dimer sizing agent with the paper making fibers;
 - (c) combining a surface active agent with the paper making fibers; and,
 - (d) removing the water from the aqueous slurry.
- 19. The method of claim 18, in which the ketene dimer sizing agent is combined with the paper making fibers prior to the removal of water from the slurry .
- 20. The method of claim 18, in which the ketene dimer sizing agent is combined with the paper making fibers after the removal of water from the aqueous slurry.
- 21. A soft highly absorbent paper product comprising a blended base sheet, a ketene dimer sizing agent, and a surface active agent.
- 22.(as amended by Preliminary Amendment) The soft highly absorbent paper product of claim 21, in which there are at least 1 ½ pounds of the sizing agent per ton of paper product, and the product has a water absorbency rate of less than 10 seconds.